

### Radiography test report

<b>Report number</b>	LW21-1306-2 RT
<b>Customer name</b>	Asme Welding Pty Ltd
<b>Address</b>	14 Industrial Drive Sunshine VIC Australia 3020
<b>Requested by</b>	Kenny Nguyen
<b>Purchase Order</b>	PO-1782
<b>Accredited laboratory</b>	LMATS Melbourne Laboratory
<b>Test date</b>	14/07/2021
<b>Job address</b>	LMATS Melbourne Laboratory
<b>Job description</b>	Radiographic Inspection of Welder Qualification Coupon
<b>Identification</b>	DOW-034
<b>Material grade</b>	ASTM A106/A106M-18 Grade B
<b>Test specification</b>	AS 3992:2020 - Clause 6.1.5 (WPWQ qualification)
<b>Test method</b>	AS 2177-2006 (R2016) X-ray
<b>Test procedure</b>	TP-RT-03 (I1,R6)
<b>Imaging film/device</b>	AGFA Structurix D7
<b>Image processing</b>	Automatic, Viewer L002538
<b>IQI type</b>	AS 2314 Fe(1) 10
<b>Intensifying screens</b>	0.02mm thick Pb at front and back,
<b>Surface condition</b>	As welded
<b>Test equipment</b>	X-ray L0550
<b>Approved tester</b>	Ben Ross (AINDT RT MT PT L2)
<b>Interpreted</b>	Ben Ross (AINDT RT MT PT L2)



**Accredited for compliance with  
-Testing**

#### Signatory

(M.E.(Mech) B.Eng, ASNT L3 - UT  
MT PT, AINDT L2 PAUT UT ET RT  
MT PT)

**Mir Katouzi**  
**19/07/2021**

LW21-1306-2 RT AsmeWeldingPtyLtd Report  
LW21-1306-2 RT AsmeWeldingPtyLtd Report  
LW21-1306-2 RT AsmeWeldingPtyLtd Report  
LW21-1306-2 RT AsmeWeldingPtyLtd Report  
LW21-1306-2 RT AsmeWeldingPtyLtd Report  
LW21-1306-2 RT AsmeWeldingPtyLtd Report



Table 1: Test area identification (provided by the client) and results (All dimensions are in mm)

Identification	Weld No.	Material Grade	Pipe size	Thickness	PQR/WPS No.	Welder name (ID)	Weld type	Technique	Radiograph No.	Interpretation	Density range	Required Sensitivity	Achieved sensitivity	Result
WQ-AP052-2	WELD 01	A106	100 NB	6.02mm	AWS-WP-004	AP-052	Butt	XR2/DWD	187-225, 225-300, 300-0	A, GPs, A	1.9-3.3	W11	W13, 2.6%	C

**Test restrictions** Nil

**Comments** Nil

**Notes**

1. All test and inspection items will be discarded after 6 weeks, unless retrieved by the clients representative
2. Samples, identification of samples and all job specific details were supplied by the client.
3. Any stated nominal pipe sizes and nominal thickness of the material were provided by the client.
4. Where applicable, the Measurement Uncertainty (MU) applies to the test results as per LMATS procedure. MU can be obtained by contacting one of the LMATS ISO 17025 accredited laboratory.
5. If this report does not specify acceptance criteria, then the test or inspection results should be referred to a competent authority for further action.
6. Refer to the attached revision notes (if this report is revised). This report shall not be reproduced except in full without approval of the issuing laboratory to ensure that parts of a report are not taken out of context. The client or their representatives shall not edit this report.
7. LMATS or its professional indemnity insurance provider do not indemnify the contents within this report or the conformity of a tested product unless the invoice for the reported work is paid in full within the agreed credit terms. Reports will be revoked if the invoice for the completed work is not paid in full.

**Abbreviations used in this report**

A - No discontinuities detected	KC - Crater crack	SED - Excessive Dressing (underflushing)
BT - Burn (melt) Through	KL - Longitudinal crack	SGI - Incompletely filled Groove
C - Comply	KT - Transverse crack	SGS - Shrinkage Groove
CP - Crater Pipe	LI - lack of Inter-run fusion	SMG - Grinding Mark
DNC - Does Not Comply	LP - Incomplete root Penetration	SMH - Hammer Mark
EC - Elongated Cavity (hollow bead)	LR - lack of Root fusion (missed edge)	SMT - Tool Mark (chipping mark)
GP - Gas Pore	LS - lack of Side fusion	SRC - Root Concavity (Suck back)
HiLo - Linear misalignment	NRRD - No Recordable Reflections Detected	SSP - Spatter
IC - Copper Inclusion	NUSID - No unacceptable Surface Indications Detected	SUC(e) - Undercut External
IL - Linear Inclusion (slag line)	p.d. - Processing / film Defects	SUC(i) - Undercut Internal
IN - Inclusion	PG - Localized Porosity	SXP - Excessive Penetration
IO - Oxide Inclusion (wagon tracks)	PL - Linear Porosity	WH - Worm Hole
IT - Tungsten Inclusion	PU - Uniform Porosity	

**End of LMATS report. Information included on the following pages (if any) was provided by the client or other parties.**